

# VICTREX<sup>®</sup> PEEK 150FW30

#### > Product Description:

High performance thermoplastic material, 30% reinforced with carbon fibre / PTFE **P**oly**E**ther**E**ther**K**etone (PEEK), semi crystalline, granules for injection moulding, easy flow, FDA food contact compliant, colour black.

### > Typical Application Areas:

Tribological applications with thin cross sections or long flow lengths for high strength. Excellent wear resistance, very low coefficient of friction, low coefficient of thermal expansion. Chemically resistant to aggressive environments.

#### Material Properties

	CONDITIONS TEST METHOD U		UNITS	TYPICAL VALUE	
Mechanical Data					
Tensile Strength	Break, 23°C	ISO 527	MPa	180	
	Break, 125°C		115		
Tensile Elongation	Break, 23°C	ISO 527	%	1.8	
Tensile Modulus	23°C	ISO 527	GPa	15.0	
Flexural Strength	23°C	ISO 178	MPa	270	
	125°C			170	
	175°C			100	
	225°C			60	
Flexural Modulus	23°C	ISO 178 GPa		14.5	
Compressive Strength	23°C	ISO 604	MPa	210	
	120°C	120°C		155	
	200°C			60	
Charpy Impact Strength	Notched, 23°C	ISO 179/1eA	kJ m⁻²	5.0	
	Unnotched, 23°C	ISO 179/1U		35	
Izod Impact Strength	Notched, 23°C	ISO 180/A	kJ m⁻²	5.0	
	Unnotched, 23°C	ISO 180/U		35	

Thermal Data				
Melting Point		ISO 11357	°C	343
Glass Transition (Tg)	Onset	Onset ISO 11357 °C		143
Specific Heat Capacity	23°C	23°C DSC kJ kg <sup>-1</sup> °C <sup>-1</sup>		1.8
Coefficient of Thermal Expansion	Along flow below Tg	ISO 11359 ppm K <sup>-1</sup>		9
	Average below Tg			45
	Along flow above Tg			9
	Average above Tg			110
Heat Deflection Temperature	1.8 MPa	ISO 75-f	°C	325

Flow				
Melt Viscosity	400°C	ISO 11443	Pa.s	260
	-			
Miscellaneous				
Density	Crystalline	ISO 1183	g cm <sup>-3</sup>	1.43
Shore D hardness	23°C	ISO 868		84.5
Water Absorption (3.2mm thick Tensile bar)	24h, 23°C	ISO 62-1	%	0.04
(by immersion)	Equilibrium, 23°C			0.3

## www.victrex.com



Electrical Properties				
Volume Resistivity	23°C, 1V IEC 60093 Ω cm		10 <sup>7</sup>	
	-	-		
	1			
Recommended Processing Conditions				
Drying Temperature / Time	150°C / 3h or 120°C / 5h			
Temperature settings	365 / 370 / 375 / 380 / 385°C (Nozzle)			
Hopper Temperature	Not greater than 100°C			
Mould Temperature	170°C - 200°C (max 250°C)			
Runner	Die / nozzle >3mm, manifold >3.5mm			
Gate	>2mm or 0.5 x part thickness			

Mould Shrinkage and Spiral Flow					
Spiral Flow	385°C nozzle, 180°C tool	1mm thick section	Victrex	mm	165
Mould Shrinkage	385°C nozzle, 180°C tool	Along flow	ISO 294-4	%	0.1
		Across flow			0.6

Important note:

Data are generated in accordance with prevailing national, international and internal standards, and should be used for material comparison. Actual property values are highly dependent on part geometry, mould configuration and processing conditions. Properties may also differ for along flow and across flow directions

Detailed data available on our website www.victrex.com or upon request

#### **World Headquarters**

Victrex plc, Hillhouse International, Thornton Cleveleys, Lancashire FY5 4QD United Kingdom Tel: + (44) 1253 897700 Fax: + (44) 1253 897701 Email: victrexplc@victrex.com

VICTREX PLC BELIEVES THAT THE INFORMATION CONTAINED IN THIS BROCHURE IS AN ACCURATE DESCRIPTION OF THE TYPICAL CHARACTERISTICS AND/OR USES OF THE PRODUCT OR PRODUCTS, BUT IT IS THE CUSTOMER'S RESPONSIBILITY TO THOROUGHLY TEST THE PRODUCT IN EACH SPECIFIC APPLICATION TO DETERMINE ITS PERFORMANCE, EFFICACY AND SAFETY FOR EACH END-USE PRODUCT, DEVICE OR OTHER APPLICATION, SUGGESTIONS OF USES SHOULD NOT BE TAKEN AS INDUCEMENTS TO INFRINGE ANY PARTICULAR PATENT. THE INFORMATION AND DATA CONTAINED HEREIN ARE BASED ON INFORMATION WE BELIEVE RELIABLE. MENTION OF A PRODUCT IN THIS DOCUMENTATION IS NOT A GUARANTEE OF AVAILABILITY. VICTREX PLC RESERVES THE RIGHT TO MODIFY PRODUCTS, SPECIFICATIONS AND/OR PACKAGING AS PART DF A CONTINUOUS PROGRAM OF PRODUCT DEVELOPMENT. VICTREX<sup>®</sup> IS A REGISTERED TRADEMARK OF VICTREX MANUFACTURING LIMITED. VICTREX PLS A TRADEMARK OF VICTREX MANUFACTURING LIMITED. PEEK-ESD<sup>™</sup>, HT<sup>™</sup>, ST<sup>™</sup> AND WG<sup>™</sup> ARE TRADEMARK OF VICTREX PLC. VICOTE<sup>®</sup> AND APTIV<sup>®</sup> ARE REGISTERED TRADEMARKS OF VICTREX PLC.



VICTREX PLC MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, A WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR OF NTELLECTUAL PROPERTY NON-INFRINGEMENT, INCLUDING, BUT NOT LIMITED TO PATENT NON-INFRINGEMENT, WHICH ARE EXPRESSI PRIMPLIED, IN FACT OR BY LAW, FURTHER, VICTREX PLC MAKES NO WARRANTY TO YOUR CUSTOMERS OR GENTS, AND HAS NOT AUTHORIZED ANYONE TO MAKE ANY REPRESENTATION OR WARRANTY OTHER THAN AS PROVIDED ABOVE, VICTREX PLC SHALL IN NO EVENT BE LIABLE FOR ANY GENERAL, INDIRECT, SPECIAL SONSEQUENTIAL, PUNITIVE, INCIDENTIAL OR SIMILAR DAMAGES, INCLUDING WITHOUT LIMITATION, DAMAGES FOR HARM TO BUSINESS, LOST PROFITS OR LOST SAVINGS, EVEN IF VICTREX HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES, REGARDLESS OF THE FORM OF ACTION.